

# EASYFIT®

**UPVC Plumbing Systems** 

# KEEPS YOUR DRINKING WATER LEAD-FREE & YOU, TENSION-FREE.





Pipes as per: ASTM D 1785 (SCH 40 & SCH 80)

Fittings as per:
ASTM D 2466 (SCH 40)
ASTM D 2467 (SCH 80)




### **Product range**

• Pipes: 15 to 250mm (1/2 to 10 inch) • Fittings: 15 to 150mm (1/2 to 6 inch) • Solvent Cement: Tin: 50ml to 1liter | Tube: 25 & 50ml

#### **Standards**

Pipes				Fittings			
Size (mm)	Class	Standard	End Connection	Size (mm)	Class	Standard	End Connection
15 to 250	SCH - 40	ASTM D - 1785	and	15 to 150	SCH - 40	ASTM D 2466	Solvent Cement Socket Joint.     For transition joints, fittings with plastic threads & metal threaded inserts are available.
15 to 250	SCH - 80	ASTM D - 1785		15 to 100	SCH - 80	ASTM D 2467	



#### Features and benefits

- Proven performance for water temperature from 5°C to 60°C
- Lead-free material ensures safe drinking water
- Self-extinguishing. Does not support combustion
- Fast and easy installation. Saves labour

## **Dimensions**

Dimensional & working pressure details for Easyfit UPVC Pipes (Solvent Weld) at 23°C

Nominal Bore		Outside	Sch-	40	Sch-80	
		Diameter	Wall Thickness	Working Pressure	Wall Thickness	Working Pressure
(mm)	(inch)	(mm)	(mm)	(Kg/cm²)	(mm)	(Kg/cm²)
15	1/2	21.34 +/- 0.10	2.77 + 0.51	42.40	3.73 + 0.51	59.75
20	3/4	26.67 +/- 0.10	2.87 + 0.51	33.75	3.91 + 0.51	48.50
25	1	33.40 +/- 0.13	3.38 + 0.51	31.60	4.55 + 0.53	44.25
32	1 1/4	42.16 +/- 0.13	3.56 + 0.51	26.00	4.85 + 0.58	36.60
40	1 ½	48.26 +/- 0.15	3.68 + 0.51	23.25	5.08 + 0.61	33.00
50	2	60.32 +/- 0.15	3.91 + 0.51	19.65	5.54 + 0.66	28.10
65	2 1/2	73.02 +/- 0.18	5.16 + 0.61	21.10	7.01 + 0.84	29.55
80	3	88.90 +/- 0.20	5.49 + 0.66	18.25	7.62 + 0.91	26.00
100	4	114.30 +/- 0.23	6.02 + 0.71	15.50	8.56 + 1.02	22.50
150	6	168.28 +/- 0.28	7.11 + 0.86	12.60	10.97 + 1.32	19.65
200	8	219.10 +/- 0.38	8.18 + 0.99	11.20	12.70 + 1.52	17.50
250	10	273.00 +/- 0.38	9.27 + 1.12	9.90	15.06 + 1.80	16.20

Working pressure details for Easyfit UPVC Fittings (Solvent Weld) at 23°C

		Sch-40	Sch-80	
Nomin	al Bore	Working Pressure	Working Pressure	
(mm)	(inch)	(Kg/cm²)	(Kg/cm²)	
15	1/2	25.30	35.85	
20	3/4	20.25	29.10	
25	1	18.95	26.55	
32	1 1/4	15.60	21.95	
40	1 ½	13.95	19.80	
50	2	11.75	16.85	
65	21/2		17.70	
80	3		15.60	
100	4		13.50	
150	6	7.50		

Working pressure for Metal Insert Fittings is 15Kg/cm<sup>2</sup>

Note: • For threaded pipes & fittings, the working pressure at 23°C shall be considered as 50% of rating

• Pressure rating of UPVC pipes & fittings is temperature related. Derating factor shall be applied for applications at higher temperatures